

USSN: 09/838,884Attorney Docket No.: 117-P-1345US11**Amendments to the Claims**

A detailed list of all claims under examination is set out below. Please amend claim 28 as shown below in marked form and add new claims 36-41 as shown below:

1. (withdrawn): A coated substrate comprising a strippable intermediate coating atop the substrate and a strip agent-permeable waterborne overcoat adhered to the intermediate coating, wherein the dried overcoat is less strippable and more wear-resistant than the dried intermediate coating.
2. (withdrawn): A coated substrate according to claim 1, wherein the substrate comprises a floor.
3. (withdrawn): A coated substrate according to claim 2, wherein the substrate comprises a resilient flooring material.
4. (withdrawn): A coated substrate according to claim 3, wherein the substrate comprises a vinyl or vinyl composite tile.
5. (withdrawn): A coated substrate according to claim 1, wherein the substrate comprises a wall, ceiling, label, emblem, sign or vehicle.
6. (withdrawn): A coated substrate according to claim 1, wherein the intermediate coating comprises a metal-catalyzed acrylic.
7. (withdrawn): A coated substrate according to claim 1, wherein the intermediate coating has a strippability rating of 6 or more on a 7 point scale, corresponding to at least partial strip with softened coating in all areas, using a test strip agent made using a 25% water solution of a concentrate that contained 59% softened water, 6% sodium xylene sulfonate, 4.5% potassium hydroxide, 10% monoethanolamine, 0.2% tetrasodium EDTA, 10% ethylene glycol phenyl ether and 0.05% fluorosurfactant, and a 10 minute standing time.

USSN: 09/838,884

Attorney Docket No.: 117-P-1345USII

8. (withdrawn): A coated substrate according to claim 1, wherein the intermediate coating has a thickness of about 2.5 to about 75 micrometers.
9. (withdrawn): A coated substrate according to claim 1, wherein the overcoat comprises an emulsion, suspension or dispersion.
10. (withdrawn): A coated substrate according to claim 1, wherein the overcoat is radiation curable.
11. (withdrawn): A coated substrate according to claim 1, wherein the overcoat is UV-curable.
12. (withdrawn): A coated substrate according to claim 1, wherein the overcoat comprises an acrylate, urethane or acrylated urethane.
13. (withdrawn): A coated substrate according to claim 12, wherein the overcoat comprises an aromatic urethane.
14. (withdrawn): A coated substrate according to claim 12, wherein the overcoat comprises an aliphatic polyester urethane.
15. (withdrawn): A coated substrate according to claim 1, wherein the overcoat is not metal crosslinked.
16. (withdrawn): A coated substrate according to claim 1, wherein the dried overcoat has a strippability rating of 4 or less on a 7 point scale, corresponding to no more than severe chemical attack on the overcoat and the onset of stripping, using a test strip agent made using a 25% water solution of a concentrate that contained 59% softened water, 6% sodium xylene sulfonate, 4.5% potassium hydroxide, 10% monoethanolamine, 0.2% tetrasodium EDTA, 10% ethylene glycol phenyl ether and 0.05% fluorosurfactant, and a 30 minute standing time.
17. (withdrawn): A coated substrate according to claim 1, wherein the dried overcoat has a thickness of about 2.5 to about 75 micrometers.

USSN: 09/838,884Attorney Docket No.: 117-P-1345USU1

18. (withdrawn): A coated substrate according to claim 1, wherein the overcoat comprises two or more different layers of materials.
19. (withdrawn): A coated substrate according to claim 1, wherein the substrate comprises a floor and the overcoat is UV curable.
20. (withdrawn): A strippable laminate finish kit, comprising one or more containers of a strippable intermediate coating and a strip agent-permeable waterborne overcoat, wherein the dried overcoat adheres to the intermediate coating and is less strippable and more wear resistant than the dried intermediate coating.
21. (withdrawn): A strippable laminate finish kit according to claim 20, further comprising a strip agent.
22. (withdrawn): A strippable laminate finish kit according to claim 20, wherein the overcoat comprises a one-part photopolymerizable material.
23. (withdrawn): A strippable laminate finish kit according to claim 20, wherein the overcoat comprises a UV curable material.
24. (withdrawn): A strippable laminate finish kit according to claim 20, wherein the overcoat comprises an acrylate, urethane or acrylated urethane.
25. (withdrawn): A strippable laminate finish kit according to claim 20, wherein the overcoat comprises an aromatic urethane.
26. (withdrawn): A strippable laminate finish kit according to claim 20, wherein the overcoat comprises an aliphatic polyester urethane.

USSN: 09/838,884

Attorney Docket No.: 117-P-1345USI1

27. (withdrawn): A strippable laminate finish kit according to claim 20, wherein:
- a) the intermediate coating has a strippability rating of 6 or more on a 7 point scale, corresponding to at least partial strip with softened coating in all areas, and
  - b) the overcoat has a strippability rating of 4 or less on a 7 point scale, corresponding to no more than severe chemical attack on the overcoat and the onset of stripping, using a test strip agent made using a 25% water solution of a concentrate that contained 59% softened water, 6% sodium xylene sulfonate, 4.5% potassium hydroxide, 10% monoethanolamine, 0.2% tetrasodium EDTA, 10% ethylene glycol phenyl ether and 0.05% fluorosurfactant, and a 10 minute standing time.
28. (currently amended): A method for applying a renewable finish to a substrate floor, comprising:
- a) applying to the substrate floor a strippable intermediate coating;
  - b) drying the intermediate coating until it is dry to the touch; and
  - c) applying a strip agent-permeable waterborne overcoat to the dried intermediate coating and drying or otherwise hardening the overcoat; wherein the dried or otherwise hardened overcoat adheres to the dried intermediate coating and is less strippable and more wear resistant than the dried intermediate coating.
29. (original): A method according to claim 28, wherein the overcoat comprises an emulsion, suspension or dispersion.
30. (original): A method according to claim 28, wherein the overcoat comprises an acrylate, urethane or acrylated urethane.
31. (original): A method according to claim 28, wherein the overcoat is UV curable.
32. (original): A method according to claim 31, wherein the overcoat is applied in two or more coats each of which is UV cured before application of any further coat.

USSN: 09/838,884Attorney Docket No.: 117-P-1345US11

33. (original): A method for removing a multilayer finish, comprising:
- a) applying a strip agent to a dried waterborne radiation cured overcoat adhered to a dried intermediate layer atop a substrate;
  - b) allowing the strip agent to permeate through the overcoat to attack the intermediate layer; and
  - c) removing the intermediate layer and overcoat without removing substantial portions of the underlying substrate.
34. (previously presented): A method according to claim 33, wherein permeation of the strip agent through the overcoat is enhanced by mechanically roughening the overcoat prior to applying the strip agent.
35. (original): A method according to claim 33, wherein removal of the intermediate layer and overcoat occurs in less than 10 minutes after application of the strip agent.
36. (new): A method according to claim 28, wherein the floor comprises resilient flooring material.
37. (new): A method according to claim 28, wherein the floor comprises vinyl flooring or vinyl composite tiles.
38. (new): A method according to claim 28, comprising applying the intermediate coating and overcoat using a mop.
39. (new): A method according to claim 33, wherein the substrate comprises a floor.
40. (new): A method according to claim 39, wherein the floor comprises resilient flooring material.
41. (new): A method according to claim 39, wherein the floor comprises vinyl flooring or vinyl composite tiles.